

SIMONA® HDPE Boat Board®

Proven in extreme marine conditions. Maintenance-free integral colors. Long-term durability for boat building components, outdoor and indoor cabinetry.



SIMONA® HDPE Boat Board® sets the high bar for its combination of long-term performance, durability, appearance and fabrication ease and consistency.

In boat building components, this tough, UV resistant sheet withstands long term exposure to intense sun, salt water and rigorous use. This also makes it ideal for outdoor patio, poolside and marina cabinetry, furniture and accessories. Its impact resistance, FDA compliance, easy-to-clean surface and attractive appearance enhance indoor medical, clinical and laboratory cabinetry as well.

Unlike plywood, SIMONA HDPE Boat Board won't delaminate, rot or splinter, and its integral colors hide scratches and marring that ruin painted surfaces. Its stain resistance, easy-to-clean matte finish and wide spectrum of integral colors further assure long lasting appearance and functionality.

In fabrication, it maintains exceptional flatness and dimensional stability for high production yields and finished part quality. Standard woodworking equipment works well with the material, and fabricators appreciate its advantages especially in thicker gauges for large flat, formed or machined panels.

Advantages

- Integral color hides marring, scratches
- Solid polymer composition won't delaminate, rot or splinter
- Uniform color and surface consistency
- Maintenance-free, easy to clean
Resists impacts, extreme weather
- Easy to fabricate using standard woodworking tools

Applications

- Instrument panels
- Instrument and control base plates
- Deck and seating components
- Doors, hatch and well covers
- Tables, trim, cabinets
- Storage and tackle bins
Cup and rod holders
- Steps, grab rails

Configurations

- Sheet sizes
 - 54 x 96 in. (1,372 x 2,440 mm)
- Gauges
 - 1/4; 3/8; 1/2; 3/4; 1.0 in.
(6.4; 9.5; 12.7; 19.0; 25.4 mm)
- Colors
 - Polar white; Bright white
 - Dolphin gray; Glacier gray
 - Seafoam; Sandshade
 - Brown; Black
- Texture: Matte 2 sides
- Masking: 1 side
- Custom colors, sizes: On request



SIMONA® HDPE Boat Board® offers exceptional flatness, stability and consistency in machining and fabrication.

PROPERTIES SIMONA® HDPE Boat Board®

PROPERTY, Units of Measure ¹	Test Method	TYPICAL VALUES	
		SIMONA®HDPE Boat Board	
Specific Gravity	ASTM D792	0.97	
Water Absorption, %	ASTM D570	<0.1	
MECHANICAL			
Tensile Strength @ Yield	ASTM D638	4,400 psi	30.4 MPa
Elongation @ Break, %	ASTM D638	>300%	
Flexural Modulus	ASTM D790	240,000 psi	1,655 MPa
Notched Izod Impact	ASTM D256	2.75 ft-lb/in.	146.8 J/m
Hardness, Shore D	ASTM D2240	68	
Abrasion Resistance mg/1000	Taber CS 17	-	
Coefficient of Expansion x10 ⁵	ASTM D696	10.0	
THERMAL			
Continuous Service Temperature	Maximum	170 °F	76.7 °C
Melting Point	ASTM D3418	267 °F	130.7 °C
Heat Deflection Temp. @ 66 psi (0.45 MPa)	ASTM D648	167 °F	75 °C
Heat Deflection Temp. @ 264 psi (1.8 MPa)	ASTM D648	110 °F	43.4 °C
FDA			
FDA reg. 21 Chapter 1 part 177.2510	-	Yes	

¹All tests at 73 °F (22.8 °C) in dry conditions unless otherwise noted.

SIMONA® PE, PP AND PVC FOR MACHINING AND FABRICATION

SIMONA® Polypropylene, polyethylene sheet and rod

- SIMONA® Polypropylene homopolymer
- SIMONA® Polypropylene copolymer
 - Natural, white, black, eurogrey
- SIMONA® HDPE and HDPE Boat Board
 - Natural white, black, custom colors
- SIMONA® HDPE dual color
 - Outer "skin" color, contrasting color core

SIMONA® PVC sheet and rod

- SIMONA® PVC Type I & Type II
 - White, black, gray, colors
 - Clear

SIMONA® CPVC sheet

- White, gray
- Clear

UL 94 V-0 and FM 4910 flammability test compliant
PP, PVC and CPVC grades available.



SIMONA offers the widest product range of PVC sheet and rod – FM 4910 rated sheet – chemical resistant materials from PVC, PP and PE to fluoropolymers – orthotics and prosthetics sheet – Boltaron® aircraft sheet – plus proven products for boat building, outdoor furniture and many other industries.

DISCLAIMER AND LIMITATION OF WARRANTY:

All information contained herein is believed by SIMONA AMERICA Industries to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA AMERICA Industries makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA AMERICA Industries and SIMONA Boltaron Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED.

Distributed by:



Call: 1 (866) 437-7427
Email: info@polymershapes.com
www.polymershapes.com