

TECAFORM AH LM white - Stock Shapes

Chemical Designation

POM-C (Polyacetal (Copolymer))

Colour

white

Density

1.42 g/cm³

Fillers

Proprietary

Main features

- laser-markable
- resistant to cleaning agents
- high strength
- high toughness
- good machinability
- good slide and wear properties

Target Industries

- food processing
- conveyor technology
- mechanical engineering
- precision engineering
- automotive industry
- electrical engineering
- home appliances
- medical technology

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@73°F	293,800	psi	ASTM D 638	
Tensile strength	@73°F	8200	psi	ASTM D 638	
Elongation at yield	@73°F	10	%	ASTM D 638	
Elongation at break	@73°F	54	%	ASTM D 638	
Flexural strength	@73°F	11,200	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@73°F	375,200	psi	ASTM D 790	
Compression strength	@ 10% Deformation	12,260	psi	ASTM D 695	
Compression strength	@ 1% Deformation	2700	psi	ASTM D 695	
Compression modulus	@73°F	265,000	psi	ASTM D 695	
Impact strength (Izod)	@73°F, notched	1.14	ft-lbs/in	ASTM D 256	
Rockwell hardness	@73°F	85		ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Melting temperature		336	°F	ASTM D 3418	(1) Public Source Individual Testing Recommended
Service temperature	Long Term	212	°F	-	1)
Service temperature	Short Term	284	°F	-	2)
					(2) Public Source Individual Testing Recommended
<i>Other properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs	0.12	%	ASTM D 570	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Date: 2018/10/08

Version: A0

Distributed by:



Call: 1 (866) 437-7427
 Email: info@polymershapes.com
www.polymershapes.com