

Mitsubishi Chemical Advanced Materials Proteus® White Homopolymer Polypropylene (ASTM Product Data Sheet)
Categories: Polymer; Thermoplastic; Polypropylene (PP); Polypropylene, Molded

Material Notes: Quadrant Engineering Plastic Products is now Mitsubishi Chemical Advanced Materials.

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D792
Water Absorption	<= 0.010 %	<= 0.010 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	<= 0.010 %	<= 0.010 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	78	78	ASTM D2240
Tensile Strength	33.1 MPa	4800 psi	ASTM D638
Tensile Strength at 65°C (150°F)	2.76 MPa	400 psi	ASTM D638
Tensile Strength, Yield	27.6 MPa	4000 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Tensile Modulus	1.19 GPa	173 ksi	ASTM D638
Flexural Strength	33.1 MPa	4800 psi	ASTM D790
Flexural Modulus	1.24 GPa	180 ksi	ASTM D790
Compressive Strength	34.5 MPa	5000 psi	10% Def.; ASTM D695
Compressive Modulus	1.38 GPa	200 ksi	ASTM D695
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.25	0.25	Dry vs. Steel; QTM55007

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistivity per Square	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ASTM D257

Thermal Properties	Metric	English	Comments
Melting Point	164 °C	327 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	98.9 °C	210 °F	ASTM D648
Flammability, UL94	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	Estimated Rating

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	Yes	Yes	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Acceptable	Acceptable	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Unacceptable	Unacceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Unacceptable	Unacceptable	
Hydrocarbons - Aromatic	Unacceptable	Unacceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Unacceptable	Unacceptable	

Descriptive Properties			
Color		White	
Machinability		3	1-10, 1=Easier to Machine



Email: info@polymershapes.com

Call: 1 (866) 437-7427

www.polymershapes.com