

SAFETY DATA SHEET

1. PRODUCT AND COMPANY IDENTIFICATION

PRODUCT NAME: MECHETEC® Nylon Rg-30 30% Glass Fiber filled Nylon 6/6

PRODUCT USE: Engineering/Industrial grade thermoplastic stock shapes for subsequent machining and fabrication.

MANUFACTURER: Polymer Industries
10526 AL Hwy 40
Henagar, AL 35978
Website: www.polymerindustries.com

PHONE NUMBERS: (256) 657-5197

2. HEALTH HAZARDS IDENTIFICATION

ACUTE OR IMMEDIATE EFFECTS/ROUTES OF EXPOSURE:

SKIN: Hot or molten nylon may cause thermal burns.
EYES: Contact with powder or dust may cause mechanical irritation.
INHALATION: Shapes are not considered an inhalation hazard.
INGESTION: Not a probable route of exposure.



LONG TERM/DELAYED EFFECTS: None Known.

MEDICAL RESTRICTIONS: None Known

MEDICAL CONDITIONS AGGRAVATED BY EXPOSURE: None Known.

CHRONIC EFFECTS: There are no known effects from exposure to MECHETEC® Nylon Rg-30 polymer itself. Significant skin permeation and systemic toxicity after contact appears unlikely. There are inconclusive or unverified reports of human sensitization.

CHRONIC/CARCINOGENICITY: None Known.

3. COMPOSITION / INFORMATION ON INGREDIENTS

<u>INGREDIENT NAME /CHEMICAL NAME</u>	<u>CAS NUMBER</u>	<u>WEIGHT %</u>
Nylon 6/6 (Polyhexamethylene Adipamide)	32131-17-2	>55
Nylon 6 (Polycaprolactam)	25038-54-4	<15
Glass Fibers	65997-3	30+/-3

SECTION 313 SUPPLIER NOTIFICATION:

This product is not known to contain toxic chemicals listed under Section 313 of Title III of the Superfund Amendments and Reauthorization Act (SARA) of 1986 and 40CFR part 372.

4. FIRST AID MEASURES

SKIN:	If hot or molten polymer contacts skin, cool rapidly with cold water. Do not attempt to peel molten polymer from skin. Obtain medical attention for thermal burns.
EYES:	In case of eye contact, immediately flush eyes with plenty of water for at least 15 minutes. Consult a physician if symptoms persist.
INHALATION:	If exposure to fumes from overheating, move to fresh air. Consult a physician if symptoms persist.

5. FIRE FIGHTING MEASURES

AUTOIGNITION TEMPERATURE: 400 C (752 °F). Method ASTM D1929

CONDITIONS OF FLAMMABILITY: Burns with an invisible flame.

HAZARDOUS PRODUCTS OF COMBUSTION:

At temperatures above 340 C (644 °F): heavy fuming, carbon monoxide, carbon dioxide, ammonia, and oxides of nitrogen. At temperatures above 349 C (660 °F): Hydrogen Cyanide.

EXTINGUISHING MEDIA: Water spray or any class A extinguishing agent.

SPECIAL FIRE FIGHTING INSTRUCTIONS / PRECAUTIONS:

Fire fighters and others exposed to products of combustion should wear full protective clothing including self – contained, breathing apparatus. Fire fighting equipment should be thoroughly decontaminated after use.

6. ACCIDENTAL RELEASE MEASURES

SPILL OR RELEASE: Clean up by vacuuming or sweeping to prevent falls.

7. HANDLING AND STORAGE

HANDLING: Open containers only in well-ventilated area.

STORAGE: Dry storage. Keep containers closed to prevent contamination.

8. EXPOSURE CONTROLS / PERSONAL PROTECTION

VENTILATION: Local exhaust at processing equipment to keep particulates below 15 mg/m³, the OSHA limits for nuisance dusts. Grinding and machining of parts should be reviewed to assure that particulate levels are kept below recommended standards.

8. EXPOSURE CONTROLS / PERSONAL PROTECTION (continued)

PROTECTIVE EQUIPMENT:

SKIN: Protective gloves are required when handling hot polymer. Long sleeve cotton shirt and long pants when handling molten polymer.

EYE: Safety glasses are recommended to prevent particulate from entering eyes while grinding or machining.

RESPIRATOR: None under normal processing, if ventilation is adequate. If temperatures exceed 340 C/644 °F) a properly fitted NIOSH approved respirator is required.

EXPOSURE GUIDELINES: Grinding and machining of parts should be reviewed to assure that particulate levels are kept below recommended standards.

<u>INGREDIENT</u>	<u>AGENCY</u>	<u>VALUE</u>
NUISANCE/PARTICULATES	ACGIH TLV	10 mg/ m ³ /total 3 mg/ m ³ /respirable
NUISANCE/INERT DUST	OSHA PEL	15 mg/ m ³ /total 5 mg/ m ³ /respirable

9. PHYSICAL AND CHEMICAL PROPERTIES

APPEARANCE: Stock shape may be rods or plates of different sizes. White/cream color.

ODOR: Essentially odorless.

PERCENT VOLATILES: Negligible (<1% wt.).

MELTING POINT: 250-265 C (482-509 °F)

SOLUBILITY IN WATER: Negligible (<0.1%)

SPECIFIC GRAVITY: 1.25

10. STABILITY AND REACTIVITY

CHEMICAL STABILITY: Stable at normal temperatures and storage conditions.

CONDITIONS TO AVOID: Heating above 340 C (644 °F).

MATERIALS TO AVOID: Strong acids, bases, and oxidizing agents.

11. TOXICOLOGICAL INFORMATION

CHRONIC TOXICITY: MECHETEC® Nylon Rg-30 extruded shapes are harmless.

MEDICAL CONDITIONS PRONE TO AGGRAVATION BY EXPOSURE:

Thermal decomposition products of Nylon have been reported to be irritating to the mucus membranes and respiratory tract.

12. ECOLOGICAL INFORMATION

AQUATIC TOXICITY: Toxicity is expected to be low based on insolubility of polymer in water.

13. DISPOSAL CONSIDERATION

WASTE DISPOSAL: Preferred options for disposal are: recycling, incineration with energy recovery, and landfill. Treatment and disposal must be in accordance with federal, state and local regulations.

14. TRANSPORT INFORMATION

DOT HAZARD CLASS: Not regulated.

SHIPPING NAME: Not Available.

15. REGULATORY INFORMATION

TSCA INVENTORY STATUS:

In compliance with TSCA inventory requirements for commercial purposes.
In compliance with GHS developed by the U.N. and adopted on March 26,2012
In compliance with OSHA revision HAZCOM standard 2012

SECTION 313 SUPPLIER NOTIFICATION (SARA TITLE III-TOXIC CHEMICALS LIST):

This product contains no known toxic chemicals subject to the reporting requirements of section 313 of the Emergency Planning and Community Right-To-Know Act of 1986 and 40 CFR372.

HMIS RATING

HEALTH	0
FLAMMABILITY	1
REACTIVITY	0
PPE	A

16. OTHER INFORMATION

PREPARED BY: Technical Team
Polymer Industries
10526 AL Hwy 40
Henagar, AL 35978 USA

REVISION DATE: **December 01, 2017**
SUPERCEDES REVISION DATED: **Rev. 5 May 18, 2015**
REVISION SUMMARY: Updated MECHETEC product brand name
from previous UNIPA name and information.

The information set forth herein has been gathered from standard reference materials and/or supplier test data and is, to the best knowledge and belief of Polymer Industries, accurate and reliable. Such information is offered solely for your consideration, investigation and verification, and it is not suggested or guaranteed that the hazard precautions or procedures mentioned are the only ones that exist. Polymer Industries makes no warranties expressed or implied, with respect to the use of such information or the use of the specific material identified herein in combination with any other material or process, and assumes no responsibility therefore.

MECHETEC® is a registered trademark of Polymer Industries

END OF SDS

Distributed by:



Call: 1 (866) 437-7427
Email: info@polymershapes.com
www.polymershapes.com